



CHARCOAL 95 XC

Charcoal 95 XC films are highly effective at reducing solar glare, whilst at the same time continuing to present a neutral, reflection-free



Warranty See the notice



Fire-resistance rating





Storage from -5°C to +40°C **3 YEARS**



REACH RoHS compliant

RESPECTED

WIDTHS AVAILABLE:



152 cm

TECHNICAL DATASHEET

Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	1 %
Visible light transmission	6 %
Reflection of external visible light	5 %
Reflection of internal visible light	5 %
Total solar energy rejected	40 %
Total solar energy rejected 2*	44 %
Solar ratio:	
Solar energy reflection	7 %
Solar energy absorption	48 %
Solar energy transmission	45 %
Reduction in Solar Glare	95 %
g-value	0.57
u-value	5.1
Shading coefficient	0.6
Installation type : Exterior	
Roll length	30,5 m
Film composition	PET
Thickness	30μ

INSTALLATION ADVICE

Vertical installation and on standard glass surface*

Clear single pane	~
Tinted single pane	Ţ
Reflective tinted single pane	~
Clear double pane	~
Tinted double pane	!
Reflective tinted double pane	~
Gas-filled double pane - Low E	Į.
STADIP EXT. clear double pane	×
STADIP INT. clear double pane	!




*Recommendations provided on the basis of a glazed surface covering up to 2.5m², contact us for definitive details or to obtain a thermal chock analysis report.

CONSTRUCTION

Colour from the outside: BLACK

- 1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning

- Dyed polyester without optical distortion
 PS adhesive, glass polymerization within 15 days
 Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 600-F0355 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

Non-contractual data. We reserve the right to modify the composition of our films at any time. Consult our warranty documents.