



## SILVER 60 XC

Silver 60 XC films are highly effective at reducing solar heat gain, whilst at the same time continuing to allow most natural light to pass through. This film provides effective protection against solar glare, whilst its one-way mirror aspect further guarantees privacy from prying eyes. Its modern design immediately lends a contemporary feel to any building exterior.



Warranty  
See the notice



Fire-resistance rating  
**M1**



Storage from -5°C to +40°C  
**3 YEARS**



European Standard EN 12600  
**3B3**



European Standard EN 1096-1  
**TESTED IN A  
LABORATORY**



REACH RoHS compliant  
**RESPECTED**

## WIDTHS AVAILABLE:

↔ **122 cm**

↔ **152 cm**

↔ **183 cm**

## TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (\*on double glazing 4-16-4)

|                                      |        |
|--------------------------------------|--------|
| Ultraviolet transmission             | 1 %    |
| Visible light transmission           | 40 %   |
| Reflection of external visible light | 31 %   |
| Reflection of internal visible light | 31 %   |
| Total solar energy rejected          | 66 %   |
| Total solar energy rejected 2*       | 71 %   |
| Solar ratio :                        |        |
| Solar energy reflection              | 34 %   |
| Solar energy absorption              | 39 %   |
| Solar energy transmission            | 27 %   |
| Reduction in Solar Glare             | 60 %   |
| g-value                              | 0.36   |
| u-value                              | 5.3    |
| Shading coefficient                  | 0.3    |
| Installation type : Exterior         |        |
| Roll length                          | 30,5 m |
| Film composition                     | PET    |
| Thickness                            | 60 µ   |

Colour from the outside : SILVER  
MEDIUM

## CONSTRUCTION

1. Hard scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester, with anti IR metal particles deposit
3. Bonding adhesive
4. High optical quality polyester
5. PS adhesive, glass polymerization within 15 days
6. Protection release liner, disposable after installation



## MAINTENANCE INSTRUCTIONS

Soapy water solution (ref. 600-F0355 Film on), do not clean for at least a month and do not apply any type of sticker or adhesive on the film.

## INSTALLATION ADVICE

Vertical installation and on standard glass surface\*

|                                |   |
|--------------------------------|---|
| Clear single pane              | ✓ |
| Tinted single pane             | ✓ |
| Reflective tinted single pane  | ✓ |
| Clear double pane              | ✓ |
| Tinted double pane             | ✓ |
| Reflective tinted double pane  | ✓ |
| Gas-filled double pane - Low E | ✓ |
| STADIP EXT. clear double pane  | ✓ |
| STADIP INT. clear double pane  | ✓ |

✓ Yes    ! Caution    ✗ Not  
recommended

\*Recommendations provided on the basis of a glazed surface covering up to 2.5m<sup>2</sup>, contact us for definitive details or to obtain a thermal chock analysis report.

*Non-contractual data. We reserve the right to modify the composition of our films at any time. Consult our warranty documents.*