




SAFE 4 XC

Safer 4 XC solvent resistant films provide highly effective protection against tags and graffiti. The film's protective qualities are not limited to solvents, it will also shield a window's surface from other acts of vandalism involving scratching or acid etching. An easy film to install and replace, it is also classed as a security film, providing protection by holding shattered glass in place in the event of an explosion or serious impact.



Warranty
 See the notice



Fire-resistance rating
M1



Storage from -5°C to +40°C
3 YEARS



REACH RoHS compliant
RESPECTED

WIDTHS AVAILABLE:

↔ **122 cm**

↔ **152 cm**

↔ **183 cm**

TECHNICAL DATASHEET


Data calculated based on film applied to clear glass 3 mm thick (*on double glazing 4-16-4)

Ultraviolet transmission	5 %
Visible light transmission	85 %
Reflection of external visible light	11 %
Reflection of internal visible light	11 %
Total solar energy rejected	19 %
Total solar energy rejected 2*	19 %
Solar ratio :	
Solar energy reflection	9 %
Solar energy absorption	14 %
Solar energy transmission	77 %
Reduction in Solar Glare	14 %
g-value	0.83
u-value	5.7
Shading coefficient	0.9
Tensile strength (kg/cm ²)	28
Elongation at break	125%
Installation type : Exterior	
Roll length	30,5 m
Film composition	PET
Thickness	120 µ

Colour from the outside :
 TRANSPARENT

CONSTRUCTION

1. "Hard" scratch resistant layer, for durability and ease of maintenance during window cleaning
2. High optical quality polyester
3. Bonding adhesive
4. High optical quality polyester
5. Reinforced PS Adhesive to accompany the elasticity of the film in case of impact, glass polymerization within 30 days
6. Protection release liner, disposable after installation



MAINTENANCE INSTRUCTIONS

Safety film with reinforced PS adhesive requiring a suitable application solution (Film On ref 600-F0355 and 2cl/litre of water) and a suitable safety squeegee 150-054/150-055/150-056. Do not clean for at least 1 month and do not apply stickers or other adhesives to the film.

Non-contractual data. We reserve the right to modify the composition of our films at any time. Consult our warranty documents.